

HRQ

HYBRID RESILIENT QUARTZ

CHEMICAL RESISTANCE CHART

ASTM F925

Staining Agent	Surface Dulling	Surface Attack	Color Change	Surface Dulling	Surface Attack	Color Change
5% Acetic Acid	0	0	0	0	0	0
70% Isopropyl Alcohol	0	0	0	0	0	0
5% Sodium Hydroxide	0	0	0	0	0	0
Sulfuric Acid	0	0	0	0	0	0
5% Hydrochloric Acid	0	0	0	0	0	0
5% Ammonia	0	0	0	0	0	0
5.25% Sodium Hypochlorite	0	0	0	0	0	0
5% Phenol	0	0	0	0	0	0
Bleach	0	0	0	0	0	0
Gasoline	0	0	0	0	0	0
Olive Oil	0	0	0	0	0	0
Noble Brio Cream Cleanser	0	0	0	0	0	0
EcoLab Milko Quat	0	0	0	0	0	0
Kerosene	0	0	0	0	0	0

- 0 - No Change
- 1 - Slight Change
- 2 - Moderate Change
- 3 - Severe Change

